



Soft

062, price group 31

Soft leather is a corrected grain where most scars and marks have been removed from the surface. The leather is easy to maintain due to a protecting layer of finish and is particularly suitable for families with children.



Thickness: 0,9 - 1,1 mm



Lightfastness: 4

PRODUCT CHARACTERISTICS	
Raw material	Overseas raw hides
Tanning	Chrome
Available colours	4

DURABILITY SPECIFICATIONS			
Test	Test specification	Unit	Test result
Light fastness	DIN EN ISO 105-B02	grade	≥ 4
Colour fastness to cycles of to-and-fro rubbing	DIN EN ISO 11640/41 500 rubs. dry	grade	4
	DIN EN ISO 11640/41 250 rubs. wet	grade	4
	DIN EN ISO 11640/41 250 rubs. sweat	grade	4
Adhesion of finish	DIN EN ISO 11644	N/cm	3
Double edge tear load of leather	DIN EN ISO 3377-2	N	40
Determination of flex resistance - Flexometer method	EN ISO 5402-1	cycles	50.000
Determination of pH and difference figure	DIN EN ISO 4045	-	≥ 3,2

PROCESSING SPECIFICATION			
Test	Test specification	Unit	Test result
Tear strength - Single edge tear	UNI EN ISO 3377-1	N	≥ 20
Colour fastness to rubbing - Dry 500 Cycles	UNI EN ISO 11640:1998	Grey Scale	≥ 4
Abriebfestigkeit - Nass 250 Zyklen	UNI EN ISO 11640:1998	Grey Scale	≥ 4
Colour fastness to rubbing - Wet 250 Cycles	UNI EN ISO 11640:1998 ISO 11641 pH8	Grey Scale	≥ 4
Flexing endurance - Dry 50.000 Cycles	UNI EN ISO 5402		No damage
Finish Adhesion - Dry	UNI EN ISO 11644	N/cm	≥ 2
Color fastness to articial light - Exposition energy 16.000 kj/sqm	UNI EN ISO 105 B02 (MET. 5)	Blue Scale	≥ 5
Smolder resistance, cigarette and match flame	CAL TB-117 (2013, Sec. 1) BS 5852: 1979, source 0-1 BS EN 1021-1-2:2006	-	Pass

Chrome-tanned and produced without the use of PCP and CFC, which are harmful to the environment. The leather complies with all limits and standards for chromium VI and the REACH declaration.